# Porous Materials of Hydroxyapatite/biopolymers Nanocomposites through Self-organization

Toshiyuki Ikoma<sup>a,b)</sup> Ichiro Sekiya<sup>c)</sup> Takeshi Muneta<sup>b,c)</sup> and Junzo Tanaka<sup>a,b)</sup>

- a) National Institute for Materials Science, Namiki 1-1, Tsukuba, Ibaraki 305-0044, Japan
- b) CREST, Japan Science and Technology Corporation, Honcho 4-1-8, Kawaguchi, Saitama 332-0012, Japan
- c) Tokyo Medical and Dental University, Yushima 1-5-45, Bunkyo, Tokyo 113-8519, JAPAN

### **Abstract**

With the advent of new treatment of tissue repairs, tissue engineering is one of the key technologies. There are three important factors; scaffold, mechanical stimulation and biochemical factor. In this study, we have developed porous materials of hydroxyapatite, polysaccharides and collagens nanocomposites as a novel scaffold in which the nanostructures were controlled through self-organization processes. The porous materials of the nanocomposites have the pore diameter of 200-300µm and a good biocompatibility to human chondrocytes.

#### Introduction

Tissues, organs and matrix in human bodies that constructed with inorganic (mainly calcium phosphate) and/or organic substances (mainly collagen) have highly ordered hierarchical structures at molecular levels. These organized structures show many intelligential functions for the lives to survive on the earth. For example, pro-collagens with *N* and *C*- terminus produced in endoplasmic of the cells are released at the outer fields and the pro-collagens are spontaneously assembled and formed the collagen fibrils with periodical structure of 67nm; the details of self-organization processes are more complex manners. In the macro region of bone, the hydroxyapatite (HAp) and collagen fibrils are highly ordered structures and bone shows strong mechanical and other specific properties. To architect the similar structures of our tissues, the formation processes of interfacial interaction governed by the competition and harmony of ionic, covalent, hydrogen and other weak bonds should be understood and controlled. In this study, we aimed to create the novel porous materials with hydroxyapatite and biopolymers (polysaccharides and collagens) under self-organization processes and examine the cell reaction properties using human chondrocytes.

## **Experiments**

Initially, we prepared HAp and polysaccharide self-organized bodies with a precipitation method. The starting substances of the polysaccharides are used as chondroitin sulfate (ChS) or hyaluronic acid (HyA). The both polysaccharides were dispersed in the calcium hydroxide suspension. The phosphate solutions were added slowly into the calcium hydroxide suspensions with polysaccharides, adjusting the pH value of 8.00 at the room temperature. The nanostructure of HAp and polysaccharides self-organized bodies were observed with transmittance electron microscopy and were characterized with Fourier-transformed infrared spectroscopy (FT-IR) and thermogravimetry (TG).

Furthermore, we conducted the hybrid of collagen with the hydroxyapatite and polysaccharides self-organized bodies with a coprecipitation method. The collagens are type I or type II collagen (I-Col and II-Col) that were dispersed into phosphate solutions. The temperature and pH at the precipitation was controlled at 40 degree and 9.00.

To fabricate the porous materials of HAp/ChS/I-Col, HAp/ChS/II-Col, HAp/HyA/I-Col and HAp/HyA/II-Col with the composition of 60:15:25, the suspensions obtained and cross-linking agencies were mixed at room temperatures and freeze dried. The microstructures of the sponges materials created were examined with scanning electron microscopy (SEM).

maintaining the data needed, and c including suggestions for reducing	nection of information is estimated to completing and reviewing the collect this burden, to Washington Headqu uld be aware that notwithstanding ar DMB control number.	ion of information. Send comments arters Services, Directorate for Infor	regarding this burden estimate mation Operations and Reports	or any other aspect of th , 1215 Jefferson Davis l	is collection of information, Highway, Suite 1204, Arlington	
1. REPORT DATE 2. REPORT TYPE N/A				3. DATES COVERED		
4. TITLE AND SUBTITLE				5a. CONTRACT NUMBER		
Porous Materials of Hydroxyapatite/biopolymers Nanocomposites through Self-organization				5b. GRANT NUMBER		
un ough Sen-organization				5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S)				5d. PROJECT NUMBER		
				5e. TASK NUMBER		
				5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  National Institute for Materials Science, Namiki 1-1, Tsukuba, Ibaraki 305-0044, Japan; CREST, Japan Science and Technology Corporation, Honcho 4-1-8, Kawaguchi, Saitama 332-0012, Japan						
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)		
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)		
12. DISTRIBUTION/AVAII Approved for publ	LABILITY STATEMENT ic release, distributi	on unlimited				
	otes 97, ARO-44924.1-E Nanotechnology)., T	*		0	nterials (5th)	
14. ABSTRACT						
15. SUBJECT TERMS						
16. SECURITY CLASSIFICATION OF: 17. LIMIT				18. NUMBER	19a. NAME OF	
a. REPORT unclassified	b. ABSTRACT <b>unclassified</b>	c. THIS PAGE <b>unclassified</b>	- ABSTRACT UU	OF PAGES 2	RESPONSIBLE PERSON	

**Report Documentation Page** 

Form Approved OMB No. 0704-0188 In-vitro evaluation system using human chondrocyte was developed to accomplish biologic evaluation for the materials semiquantatively for a short period of time. Primary cultured chondrocytes obtained during total knee arthroplasty for patients with osteoarthritis were used for biologic evaluation of the nanocomposites.

## **Results and discussion**

We synthesized nanocomposite materials of HAp and biopolymers. The composites of HAp nanocrystals and polysaccharides with carboxyl groups that widely found at the connective tissues with self-assembled structures were obtained. The TEM image of the HAp / hyaluronic acid (polysaccharide) nanocomposite is shown in Fig. 1; the corresponding diffraction patterns taken over the whole regions are given as inlet. As seen in the electron diffraction pattern, the diffraction of 002 and 004 formed clear spots along the longitudinal axis of the corresponding island-like aggregation indicated by an arrow; therefore, the *c*-axes of the constituent HAp nanocrystals were aligned in parallel with the longitudinal axis of the aggregation. The self-assembled HAp crystals on biopolymers with carboxyl groups could be explained as an epitaxial growth.




Fig. 1 TEM image of the nanocomposite of HAp and hyaluronic acid.


Fig. 2 shows one example of porous material that was fabricated like sheet. The size of the sheet was 25×15cm with the thickness of 1mm. The shape of the porous materials was easily fabricated. Fig. 3 shows the SEM images of microstructure of the nanocomposites. The averaged pore diameters were calculated to be 200-300µm.

Vigorous proliferation of the chondrocytes was observed in the composites. The rate of cell proliferation was different among the composites of different materials of hyarulonan and chondroitin sulfate, and collagen type I and type II. Cell culture test is a simple, biologic method and available for the evaluation of cell growth ratio and the production of cartilage matrix.




Fig.2 Macroscopic appearance.


Fig. 3 SEM images of porous materials of nanocomposites.




HAp/HyA/I-Col sponge



HAp/ChS/I-Col sponge



HAp/HyA/II-Col sponge



HAp/ChS/II-Col sponge